



Application Note AN-PAN-1019

Online analysis of acids and iron in pickling baths

In the galvanic industry, pickling baths are utilized to clean and remove most oxides from various steel surfaces, as well as to passivate the surface to prevent corrosion.

It is crucial to maintain specific limits for the $\text{Fe}^{2+}/\text{Fe}^{3+}$ and free acid/total acid ratios to ensure the chemical bath remains in optimal working condition. The proper composition of the baths directly affects the quality of the final products. By maintaining these

parameters within optimal ranges, the quality of the resulting products is improved, and production costs are lowered due to decreased reagent consumption.

This Process Application Note presents a method to regularly monitor the acid and iron composition in pickling baths online to ensure an even cleaning process by using a process analyzer from Metrohm Process Analytics.

INTRODUCTION

Countless products begin with steel, which is one of the most essential raw materials.

Hot-dip galvanizing (**Figure 1**) is a process that involves coating steel (or iron) with a layer of zinc to protect it from corrosion [1]. An extremely important part of steel production is the **pickling process**, in which impurities such as mill scale produced during high-temperature rolling are removed and the surface prepared for subsequent process steps. At the same time, interfering annealing colors are removed while the surface is passivated by the formation of a protective layer to protect against further corrosion.

The pickling baths used are made up of diluted acids and can vary in composition depending on the grade of steel being treated. In most cases, hydrochloric or sulfuric acid (HCl , H_2SO_4) are used, or mixtures of

acids such as HNO_3/HF or $\text{H}_2\text{SO}_4/\text{H}_3\text{PO}_4/\text{HF}$. While pickling removes impurities, the acids used also attack the steel surface and partially dissolve it. This over-pickling of the base steel can result in the **metal pitting** which leads to an undesirable rough, blistered coating in the following galvanizing steps, and also causes *excessive consumption* of the pickling acid. Dissolved iron in the form of iron oxides present in the metal oxide scale affects the pickling rate of steel as iron concentrations increase. Therefore, it is important that process-relevant parameters such as **bath composition** are controlled and maintained as accurately as possible to reduce the overconsumption of pickling chemicals while keeping the quality of the product constant.

GALVANIZING PROCESS




Figure 1. Illustration of the multi-step hot-dip galvanizing process. The pickling bath is shown in light blue.

Pickling is a highly corrosive process, and if the bath is not monitored carefully, it can lead to issues in the resulting product. Continuous online monitoring of **free and total acids** and **iron content** satisfies this requirement and as a result, pickling baths can be used more economically and ecologically. Thus, operating and chemical disposal costs are

considerably reduced.

Metrohm Process Analytics offers a multi-parameter process analyzer that is suitable for the simultaneous analysis of $\text{Fe}^{2+}/\text{Fe}^{3+}$ and free acid/total acid ratio over a wide concentration range—the **2060 TI Process Analyzer** (Figure 2).



Figure 2. 2060 TI Process Analyzer for the online analysis of critical quality parameters in pickling baths using the method of titration.

APPLICATION

Total acids, individual acids, and iron (i.e., HCl , H_2SO_4 , HNO_3 , HF , Fe_2^+ , and Fe^{3+}) were analyzed using accurate titration methods. Performance monitoring of pickling baths is possible with the use of Metrohm

process analyzers, either the 2026 HD Titrolyzer or the 2060 TI Process Analyzer, depending on whether single- or multi-parameter measurements are required.

Table 1. Parameters and their concentration ranges in pickling baths.

Parameters	Concentration [g/L]
HCl	15–250
Fe ²⁺	10–200
Fe ³⁺	1–20
HNO ₃	10–250
HF	0–100
H ₂ SO ₄	0–300

REMARKS

A settler (Figure 3) can be used as a robust preconditioning system to remove solids and particles from the liquid sample prior to the analysis.



Figure 3. Settler unit for removal of particles.

CONCLUSION

During steel production, the pickling process prepares the steel surface for subsequent finishing steps. These pickling baths contain combinations of HCl, H₂SO₄, HNO₃, HF, H₃PO₄, Fe²⁺, and Fe³⁺. For reproducible surface treatment, the bath composition must be continuously monitored. This is best done online with titration by using a rugged Metrohm process analyzer

such as the 2060 TI Process Analyzer. By supplying real-time information to the industrial control system (such as DCS or PLC) with an online process analyzer, downtimes are reduced, bath composition is optimized, and costly company assets are safeguarded.

REFERENCES

1. What is the HDG Process?. American Galvanizers Association.
<https://galvanizeit.org/hot-dip-galvanizing/hdg-process> (accessed 2023-05-08).

RELATED APPLICATION NOTES

[AN-PAN-1006](#) Determination of zinc, sulfuric acid and iron

[AN-PAN-1012](#) Online analysis of nickel ion & hypophosphite content

[AN-PAN-1018](#) Determination of acids, bases and aluminum: galvanic industry – metal surface treatment

OTHER RELATED DOCUMENTS

[WP-076](#) Process analyzers as proactive solutions for

[online corrosion monitoring](#)

BENEFITS FOR ONLINE PROCESS ANALYSIS

- **Enhanced** reproducibility, production rates, and profitability (less waste).
- **Fully automated diagnostics** – automatic alarms for when samples are out of specified concentration parameters.
- **Efficient steel pickling** at a high level of quality by constantly monitoring the processing baths.
- **Avoid unnecessary costs** by reducing the amount of time required to achieve the desired pickling results.



CONTACT

Metrohm Suisse SA
Industriestrasse 13
4800 Zofingen

info@metrohm.ch

CONFIGURATION



2060 Process Analyzer

Le 2060 Process Analyzer est un appareil d'analyse par voie humide online adapté à un grand nombre d'applications. Cet appareil d'analyse de processus propose un nouveau concept de modularité reposant sur une plate-forme centrale, dénommée « armoire de base ».

Cette armoire de base se compose de deux parties. La partie supérieure contient un écran tactile et un PC industriel. La partie inférieure contient la partie humide flexible dans laquelle est logé le matériel nécessaire à l'analyse en elle-même. Si la capacité de base de la partie humide n'est pas suffisante pour résoudre un problème d'analyse, vous pouvez ajouter jusqu'à quatre armoires de partie humide supplémentaires à cette armoire de base afin de disposer de suffisamment d'espace pour résoudre les applications les plus difficiles. Les armoires supplémentaires sont configurables de manière à ce que chaque armoire pour partie humide puisse être combinée à une armoire à réactifs avec détection de niveau intégrée (sans contact) afin d'augmenter la disponibilité de l'appareil d'analyse.

Le 2060 Process Analyzer propose différentes techniques de chimie par voie humide : le titrage, le titrage Karl Fischer, la photométrie, la mesure directe et des méthodes d'addition standard.

Pour répondre à toutes les exigences de projet (ou à tous vos besoins), des systèmes de préconditionnement d'échantillons peuvent être fournis afin de garantir une solution analytique robuste. Nous pouvons pour ainsi dire fournir tout système de pré-conditionnement d'échantillon, tels que refroidissement ou chauffage, réduction de la pression, dégazage, filtration et bien plus encore.